

## 'FASTFLOOR-IT' PUMP-APPLIED CEMENTITIOUS FLOOR SCREED

### PRODUCT DESCRIPTION

**FASTFLOOR-IT** is a revolutionary, new, highly durable, polymer-modified, pump-applied, cementitious, self-smoothing screed for floor installation and renovation, providing an extremely hard-wearing finish. When mixed with water, **FASTFLOOR-IT** gives a highly fluid, fast-setting, self-smoothing screed. It is non-hazardous and possesses a low odour.

After hardening and sealing, **FASTFLOOR-IT** gives an attractive, long lasting surface.

Fast track application methods combined with rapid strength gain enable total floor screed installation to take place over a few days.

### USES

Use **FASTFLOOR-IT** to refurbish Old, damaged concrete floors or, **alternatively**, to provide a hardwearing screed to New concrete floors.

### SPECIAL PROPERTIES

- Fast track installation
- Medium to Heavy duty
- Provides wearing surface
- Pump-applied
- Self smoothing
- Fast setting, allows early access
- Rapid strength gain
- Large area application
- Can be over-coated or tiled

### METHOD OF USE

#### Substrate Preparation

The concrete substrate should be free from oil, grease or other contamination and lightly textured. Any loosely bonded material and dust must be removed. Expansion joints, large potholes and other damage to the floor should be repaired with **CG Flooring Systems Limited** repair mortar. All movement joints must be located, re-sawn and filled with a suitable semi-rigid jointing compound after the **FASTFLOOR-IT** has been sealed. Tied joints and stable cracks should be thoroughly cleaned out (sawn with a 5mm cut if necessary) and filled with **CG Flooring Systems Limited** grout. If captive blasting is required to texture the substrate, this should be carried out **after** repairs and joint preparation to ensure a good key.

The relative humidity of the concrete substrate should not exceed 75% at time of application.

Prime the surface with a minimum of two coats of **CG Flooring Systems Limited** Screed Primer - **FASTPRIME** diluted 1 part primer to 3 parts water.

For open textured or very porous substrates the first coat of primer may be diluted 1 part primer to 5 parts water to enhance penetration into the substrate.

The **FASTPRIME** should be applied by a soft broom allowing the first coat to dry before the application of the second coat. Coverage will vary depending upon the porosity of the substrate.

The second coat of **FASTPRIME** should be touch-dry before the application of the **FASTFLOOR-IT**.

#### Application

**FASTFLOOR-IT** may be pumped using a **CG Flooring Systems Limited** floor-screed pump. The water flow rate should be adjusted to achieve the required flow (See Technical Data below). After placing, spread to the required thickness using a pin trowel. Entrapped air and residual trowel marks should be removed by use of an appropriate type of spiked roller.

**FASTFLOOR-IT** may also be applied manually. Add one 25kg unit of powder to 4.5 litres of clean water in a clean mixing vessel and mix using a slow speed drill fitted with a **CG Flooring Systems Limited** mixing paddle. Mix for a minimum of 3 minutes or until a smooth, lump-free, uniform colour consistency is achieved. Pour the mixed **FASTFLOOR-IT** onto the floor and spread to the required thickness using a steel float or pin screed. Entrapped air and residual trowel marks should be removed by use of an appropriate type of spiked roller.

Under no circumstances should the recommended water level be exceeded.

The minimum application, priming and curing temperature is 5°C. However, best results will be obtained at temperatures of between 10°C and 25°C. For temperatures outside of this range please contact **CG Flooring Systems Limited**.

#### Sealing

**FASTFLOOR-IT** should always be sealed with **CG Flooring Systems Limited** Screed Sealer – **FastSeal** between 12 and 48 hours after application is completed. The sealer should be roller applied at a rate of 10-15m<sup>2</sup> per kg with a medium or short pile roller. The formation of pools must be avoided. Once the first coat has dried a second coat of sealer must be applied. Rollers should be cleared of loose fibres before use as these may adhere to the floor. Both **FASTFLOOR-IT** and **FastSeal** should be cleaned from all tools before the material hardens.

**FASTFLOOR-IT** floors may be subject to minimal colour variation. This does not affect the performance of the floor.

*(See next page for Technical Data)*

# 'FASTFLOOR-IT' PUMP-APPLIED CEMENTITIOUS FLOOR SCREED

## TECHNICAL DATA

<b>Packaging:</b>	<b>FastPrime:</b> 5 & 10 kg packs. <b>FASTFLOOR-IT:</b> 25 kg bags. <b>FastSeal:</b> 5 & 10 kg kits	<b>Final Set:</b> 3-4 hours @ 20°C. This figure will be affected by variations in temperature.
<b>Screed Primer Ratio:</b>	<b>Normal Substrates:</b> First coat diluted 1 part to 3 parts water. Second coat diluted 1 part to 3 parts water. (2 coat system). <b>Porous Substrates:</b> First coat diluted 1 part to 5 parts water. Second coat diluted 1 part to 3 parts water. (2 coat system).	<b>Compressive Strength:</b> Tested to BS 6319:Part 2:1983 >40 N/mm <sup>2</sup> @ 28 days <b>Flexural Strength:</b> Tested to BS 6319:Part 3:1990 > 10.0 N/mm <sup>2</sup> @ 28 days <b>Shrinkage:</b> Tested to ASTM C490-00a <550 µm/m @ 28 days <b>Bond Strength:</b> > 1.5 N/mm <sup>2</sup> (to primed concrete)
<b>Screed Primer S.G:</b>	1.07 kg/ltr.	<b>Abrasion Resistance:</b> Conforms to BS 8204:Part 2:1999 'Special' Class <b>Impact Resistance:</b> Tested to BS 8204:Part 1:1999 < 1.6mm – Category A <b>Storage:</b> 6 months maximum when stored in cool, dry conditions in original, unopened containers.
<b>Coverage:</b>	<b>FastPrime :</b> 0.13 kg /m <sup>2</sup> per coat diluted 1 part primer to 3 parts water 0.15 kg /m <sup>2</sup> per coat diluted 1 part primer to 5 parts water <b>FASTFLOOR-IT:</b> 1.74 kg/m <sup>2</sup> /mm (dry powder wt) Minimum 5mm thickness. <b>FastSeal :</b> 12-20m <sup>2</sup> per kg per coat. (2 coat system)	<b>Safety:</b> <b>FASTFLOOR-IT</b> contains cement and is thus alkaline in contact with water. Prolonged exposure to the skin should be avoided. For more detailed information reference should be made to the <b>Fastfloor-IT</b> Health & Safety Data Sheet.
<b>Yield:</b>	15 litres per 25kg bag using 4.5 litres of water.	
<b>Flow:</b>	Tested using a BS 6463 Flow Mould @ 20°C Target : 170 mm [The flow mould should be placed on a flat, level surface and filled to the top with the screed material. The material should then be released by carefully lifting the flow mould from the surface. Once the material has stopped moving the diameter of the <b>FASTFLOOR-IT</b> should be measured.]	
<b>Mixing Ratio:</b>	One 25kg bag of <b>FASTFLOOR-IT</b> should be added to 4.5 litres of clean water.	
<b>Colours :</b>	Mid Grey (Natural).	
<b>Wet Density:</b>	Approx. 2100 kg/m <sup>3</sup> .	
<b>Minimum depth:</b>	5 mm.	
<b>Maximum depth:</b>	15 mm. For applications over 15mm, please contact CG Flooring Systems Limited.	
<b>Pot life:</b>	25 minutes @ 20°C. This figure will be affected by variations in temperature.	

## SPECIFICATION CLAUSE

The prepared concrete substrate shall be primed with 2 coats of CG FLOORING SYSTEMS LIMITED screed primer, **FastPrime**, diluted 1 part primer to 3 or 5 parts with water (5 parts for porous substrates – 1<sup>st</sup> coat only) and CG Flooring Systems Limited **FASTFLOOR-IT** cementitious self-smoothing screed applied when the 2<sup>nd</sup> coat of primer is touch dry. (See note 1 below). Between 12 and 48 hrs after laying, the screed shall be sealed with 2 coats of CG FLOORING SYSTEMS LIMITED screed sealer, **FastSeal**.

The **FASTFLOOR-IT** compound shall be highly fluid, fast-setting and shall have a compressive strength of >40 N/mm<sup>2</sup> and a flexural strength of >10.0 N/mm<sup>2</sup> at 28 days.

The manufacturer shall be a Registered Firm to ISO 9001.

**FASTFLOOR-IT** shall only be laid by an experienced floor screed contractor, strictly in accordance with the manufacturer's current product Technical Data Sheet, Specification and Instructions For Use.

Note 1: Permitted thickness range for CG FLOORING SYSTEMS LIMITED **Fastfloor-IT** is from 5mm to 15mm.

FFIT/tds/0306

